

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08L 95/00, C10C 3/00 C08J 3/00	A1	(11) International Publication Number: WO 94/11444 (43) International Publication Date: 26 May 1994 (26.05.94)
(21) International Application Number: PCT/SE93/00965 (22) International Filing Date: 11 November 1993 (11.11.93) (30) Priority data: 9203464-4 18 November 1992 (18.11.92) SE (71) Applicant (for all designated States except US): AKTIEBO- LAGET NYNÄS PETROLEUM [SE/SE]; Box 1021, S- 121 23 Johanneshov (SE). (72) Inventor; and (75) Inventor/Applicant (for US only) : GASTMANS, André, C., C. [BE/BE]; St. Reinhildisstraat 14, B-2640 Mortsel (BE). (74) Agents: FOGELBERG, Lennart et al.; Allied Attorneys Chemical AB, Box 27097, S-102 51 Stockholm (SE).		(81) Designated States: US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: PROCESS FOR IMPROVED HANDLING OF BITUMEN (57) Abstract The viscosity of bitumen, bitumen-like mixes based on polymer and bitumen and mixes of bitumen and additives is reduced by mixing said bitumen or mixes with at least one gas in a dynamic high shear mixer or in a static mixer.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

PROCESS FOR IMPROVED HANDLING OF BITUMEN

The present invention relates to a process for improved handling of bitumen. More particularly the present invention relates to a process for reducing the viscosity of bitumen, bitumen-like mixes based on polymer and bitumen and mixes of bitumen and additives.

Bitumen is used to make asphalt mixtures, bituminous membranes for roofings, emulsions for use in road making, anti-corrosion compositions, polymer-bitumen mixes, etc. In order to be handled in the mentioned applications, the bitumen is generally subjected to one of the following manipulations:

- A) heating of the bitumen to such an extent that it becomes more or less liquid,
- B) mixing the bitumen with solvents, or
- C) emulsifying the bitumen with water.

All these three manipulations, i.e. heating, dissolving and emulsifying, have as a goal to reduce the viscosity of the initial properties after cooling, evaporation of the solvent and breaking of the emulsion and separation of the water, respectively.

The viscosity of the bitumen is expressed in Pa.s when using a dynamic viscosimeter, in mm^2/s when using capillary viscosimeters or in other units depending upon the method used in the determination of the viscosity.

Mostly, the rheology of the bitumen at about ambient temperature is described by means of the penetration test (ASTM D5) wherein at 25°C a standard needle penetrates under a load of 100 g in 5 seconds into the bitumen. The penetration is expressed in tenths of a millimetre.

Another test comprises the measuring of the softening point. In this test (ASTM D36) a ring is filled with the bitumen to be tested and is heated under standard conditions at a constant rate of $5^{\circ}\text{C}/\text{min}$. A ball on top of the bitumen presses on the layer. When the temperature reaches a certain level, the bitumen has softened to such an extent that its deformation range has been reached. The corresponding temperature is called the ring and ball temperature (RB°) and is expressed in degrees centigrade (C°).

Each bitumen grade needs a well defined temperature or a well defined amount of solvent to reach a certain low viscosity at which it is easily handled.

The big problem, however, is that solvents cannot be used without limitations because of health and safety reasons.

Heating cannot be done in all cases without limitations either.

Thus, for instance, in road-making generation of fume limits the use of high temperatures. Also the fact that aging and hardening of the bitumen occurs in a much more dramatic way at substantially increased temperatures limits the use of heating.

Heating of a polymer-bitumen mixture to a high temperature brings the polymer in danger (depolymerisation) or destroys the homogeneity of the polymer/bitumen blend.

Heating of a hard bitumen to too high temperatures when bringing it into the form of an emulsion causes boiling of the water in the ready made emulsion.

SUBSTITUTE SHEET

Hence it is an object of the present invention to develop a process for reducing the viscosity of bitumen, bitumen-like mixes based on polymer and bitumen and mixes of bitumen and additives which process is not encumbered with the above mentioned drawbacks of the prior art methods based on heating, dissolving or emulsifying.

The present invention is based on the finding that when liquefied bitumen is milled through a mill together with a gas, the gas becomes finely distributed into the bitumen and as a result thereof causes a dramatic reduction of the viscosity. At the same time, the asphaltene clusters in the bitumen are more or less dispersed. Also this dispersion of asphaltene clusters causes a reduction of the viscosity.

In accordance with the above the present invention provides a process for reducing the viscosity of bitumen, bitumen-like mixes based on polymer and bitumen and mixes of bitumen and additives, which process is characterized in that said bitumen or mixes is/are mixed with at least one gas in a dynamic high shear mixer or in a static mixer.

The more intense the mixing, like high shear, and the thinner the layer between stator and rotor in a dynamic mixer, the bigger is the viscosity drop and the longer will this low viscosity remain, even after hot storage of the bitumen or bitumen mix for 2-4 hours. However, as indicated above, it is also possible to use static mixers in the process of the present invention but the effects on the viscosity when using static mixers are considerably lower than those obtained by means of high shear mixers.

The gas is added to the bitumen in a continuous way at the entrance of the mill and is milled together with the bitumen.

SUBSTITUTE SHEET

Depending on the final use of the bitumen or mixes it is possible to select the gas in such a way that in addition to the reduction of the viscosity also other effects are achieved.

According to one embodiment of the process according to the present invention a gas is used which is chemically inert to said bitumen or mixes. The preferred gas in this connection is nitrogen.

According to another embodiment of the process according to the present invention a gas is used which causes a change in the chemical properties of said bitumen or mixes.

For instance, air can be used as the gas which leads to semiblow bitumens. Further examples of gases which causes a chemical transformations of the bitumen or mixes, are ammonia and carbon dioxide.

Using a catalyst in combination with a gas which causes a change in the chemical properties of the bitumen or mixes will have an even more intense effect on the properties of the bitumen or mixes.

The process of the present invention can be applied to all types of bitumen such as straight run bitumens, semiblow bitumens and blown bitumens of different penetration, like 5 penetration up to several hundreds - B 1500 as an example -, bitumen-like mixes based on polymer and bitumen such as mixes with styrene-butadiene-styrene in amounts of 1 to 15 % by weight calculated on the weight of the mixture or ethylene-vinyl acetate 1-20 or others and mixes of bitumen and additives, for instance mixes of bitumen with penetrations between 5 and several hundreds and carbon black, adhesivity improvers, ageing retarders and others.

The uses of the bitumen and bitumen mixes having gas-reduced viscosity (in the following denoted "GRV-bitumen") prepared according to the invention are within the fields of making asphalt mixes, making bitumen emulsions, handling of polymer/bitumen mixes, production of roofing, anti-corrosion coating and membrane application.

The invention will now be further illustrated by means of a number of non-limitative working examples.

EXAMPLE 1

A 65 penetration bitumen, straight-run, was treated in a high shear mill from Probst und Class, Rastatt, Germany, type PUC-NA 60-RD, with nitrogen.

Temperature	:	150°C
Gap width	:	0.25 mm
Rotor speed	:	3000 rev/min
Bitumen quantity	:	0.85 l/min
Nitrogen quantity	:	not measured (free suction to open air)

The viscosity was measured at shear rate 3 sec^{-1} in a layer thickness of 1 mm - plate/plate configuration. The following results were obtained.

Temperature (C°)	Viscosity (Pa·s)	
	original	after 1 pass through mill
60	950	131
70	308	60.1
80	95.2	24.1
90	37	10.1
100	15.3	5.02
110	7.31	2.68
120	4.17	1.57
130	2.46	0.96
140	1.54	0.68

EXAMPLE 2

A 5 penetration bitumen, straight-run, was treated under the same conditions as in example 1 but at 180°C.

The viscosity was measured with CARRI-MED at shear rate 3 sec^{-1} in a layer thickness of 1 mm - plate/plate configuration. The following results were obtained.

Temperature (C°)	Viscosity (Pa·s)	
	original	after 1 pass through mill
60	1550	595
70	388	176
80	136	84
90	44.8	31.2
100	16.9	12.3
110	6.92	5.52
120	3.31	2.79
130	1.72	1.46

EXAMPLE 3

A mixture of 94 % by weight of 180/200 penetration straight-run and 6 % by weight of styrene-butadiene-styrene (Finaprene^R F 411 from Fina - Belgium), was treated in a high shear mill (from Probst und Class, Rastatt, Germany, type PUC-NA 60-RD) with nitrogen.

Temperature of bitumen mix	:	190°C
Bitumen quantity	:	0.380 l/min
Gap width	:	0.05 mm
Rotor speed	:	4000 rev/min
Nitrogen temperature	:	ambient
Nitrogen quantity	:	18 l/min

(lowest measurable quantity with present instruments).

The viscosity was measured with CARRI-MED at shear rate

3 sec⁻¹ in a layer thickness of 1 mm - plate/plate configuration. The following results were obtained.

Temperature (C°)	Viscosity (Pa·s)	
	original	after 1 pass through mill
70	672	396
80	258	152
90	10.3	61.4
100	49.5	28.0
110	14.21	9.42
120	7.69	5.32
130	2.12	2.00

EXAMPLE 4.

A 180/200 bitumen was treated with ammonia gas in a high shear mill (from Probst und Class, Rastatt, Germany, type PUC-NA 60-RD).

Temperature of bitumen mix	:	250°C
Quantity through mill	:	0.6 l/min
Ammonia temperature	:	ambient
Ammonia quantity	:	18 l/min
(lowest measurable quantity with present instruments)		
Gap width	:	0.05 mm
Rotor speed	:	4000 rev/min

The influence of the ammonia upon the bitumen was checked by measuring the acidity of the bitumen:

Original 180/200 bitumen : 3.69 mg KOH/g

1 x over mill : 3.51 mg KOH/g

2 x over mill : 2.68 mg KOH/g

3 x over mill : 2.54 mg KOH/g

SUBSTITUTE SHEET

EXAMPLE 5

A 180/200 penetration bitumen, straight-run, was treated in a static mixer (Kemics-Tubing 37-08-136, length 416 mm-21 elements from Chemineer, Derby, U.K. with air.

Penetration : original bitumen : 184
after treatment : 265

Softening point : original bitumen : 38.2°C
after treatment : 32.8°C

The viscosity was measured with CARRI-MED at shear rate 3 sec⁻¹ in a layer thickness of 1 mm - plate/plate configuration. The following results were obtained.

Temperature (C°)	Viscosity (Pa·s)	
	original	after 1 pass through mill
60	88	24.2
70	24.4	8.48
80	8.3	3.35
90	3.9	1.57
100	1.6	0.83
110	0.77	0.52
120	0.42	0.32

SUBSTITUTE SHEET

C L A I M S

1. Process for reducing the viscosity of bitumen, bitumen-like mixes based on polymer and bitumen and mixes
5 of bitumen and additives, characterized in that said bitumen or mixes is/are mixed with at least one gas in a dynamic high shear mixer or in a static mixer.
- 10 2. Process according to claim 1, characterized in that a gas is used which is chemically inert to said bitumen or mixes.
- 15 3. Process according to claim 1, characterized in that the gas is nitrogen.
- 20 4. Process according to claim 1, characterized in that a gas is used which causes a change in the chemical properties of said bitumen or mixes.
- 25 5. Process according to claim 4, characterized in that the gas is air, ammonia or carbon dioxide.
6. Process according to any of claims 4 and 5, characterized in that the bitumen or mix is mixed with the gas in the presence of a catalyst.
- 30

1
INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 93/00965

A. CLASSIFICATION OF SUBJECT MATTER

IPC5: C08L 95/00, C10C 3/00, C08J 3/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC5: C08L, C10C, C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, CA

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 5096566 (DAWSON ET AL), 17 March 1992 (17.03.92) --	1-6
A	GB, A, 2255291 (EXXON RESEARCH AND ENGINEERING COMPANY), 4 November 1992 (04.11.92) --	1-6
A	EP, A2, 0283246 (EXXON CHEMICAL PATENTS INC.), 21 Sept 1988 (21.09.88) -- -----	1-6

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"B" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

17 February 1994

21 -02- 1994

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Dagmar Järvman
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT
Information on patent family members

28/01/94

International application No.

PCT/SE 93/00965

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US-A-	5096566	17/03/92	CA-A-	1306214	11/08/92
GB-A-	2255291	04/11/92	WO-A-	9219683	12/11/92
EP-A2-	0283246	21/09/88	AU-B-	600102	02/08/90
			AU-B-	610138	16/05/91
			AU-A-	1313988	15/09/88
			AU-A-	1314088	15/09/88
			AU-A-	7193491	30/05/91
			DE-A-	3880182	19/05/93
			EP-A,B-	0283247	21/09/88